



REPORT
Intertek Testing Services NA, Inc.
1717 Arlingate Lane COLUMBUS, OHIO 43228

Project NO.: 3118569

Page 1 of 4

Revision Date: February 3rd, 2010
Original Report Date: April 23, 2007

REPORT NO. 3118569COL-001B

RENDERED TO:

IceCOLD 6601 Wickliff Trail Plano , TX 75023

STANDARD AND TEST USED: SAE J2670, Stability and Compatibility Criteria for Additives and Flushing Materials Intended for Use in Vehicle Air -Conditioning Systems Using R-134a (Proposed Draft).

AUTHORIZATION: The test was authorized by Mr. Jason Bruecker.

SPECIMEN DESCRIPTION: The tests were performed on specimen identified by the client as Ice Cold. The samples arrived in good condition. The sample has been retained until further notice from customer.

CONCLUSION: This report describes the results of IceCOLD sample in accordance with SAE J2670. The test evaluations were conducted at Intertek Testing Services located in Columbus, OH between 3/15/07 and 4/16/07. See Appendix A, B, C, and D for reported data.

Test Performed by:

Aaron Payne
Chemist
Analytical Laboratory

Report Approved by:

JOHN SCHUCHMAN
Lab Manager
Analytical Laboratory



INTERTEK TESTING SERVICES NA, cont.

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

Project No.: 3118569

Appendix A

Stability Testing

Results, Physical Properties

Tube ID	Refrigerant	Lubricant	Additive	Total Acid Number (mgKOH/g)			Refrigerant Decomposition (% by weight)			Dissolved Copper (ppm)			Dissolved Aluminum (ppm)			Dissolved Iron (ppm)		
Control	99% 134a 1% R-12	¼ PAG ¼ Mineral Oil	Blank	.05	.06	.05	<.05	<.05	<.05	2	1	2	<1	<1	<1	2	2	2
Ice Cold	99% 134a 1% R-12	¼ PAG ¼ Mineral Oil	Ice Cold	.05	.05	.04	<.05	<.05	<.05	2	2	2	<1	<1	<1	2	2	2

Results, Visual Inspections

Tube ID	Refrigerant	Lubricant	Additive	Visual Inspection, liquid phase			Visual Inspection, Copper			Visual Inspection, Steel			Visual Inspection, Aluminum			Particles/Precipitates/ Insolubles					
Control	99% 134a 1% R-12	¼ PAG ¼ Mineral Oil	Blank	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	None	None	None
Ice Cold	99% 134a 1% R-12	¼ PAG ¼ Mineral Oil	Ice Cold	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	None	None	None

Liquid Phase Visual Inspection Legend

f0 = No change f1a = Slight darkening f1b = Cloudy 1a f2a = Moderate darkening f2b = Cloudy 2a
f3a = Extreme darkening f3b = Cloudy 3a f4a = Opaque


Steel Coupon Visual Inspection Legend

f0 = No change f1 = Slight darkening f2 = Slight discoloration f3 = Moderate copper plating f4 = Heavy copper plating

Copper and Aluminum Visual Inspection Legend

f0 = No change f1 = Slight tarnish f2 = Slight corrosion f3 = Moderate corrosion f4 = Heavy corrosion

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



INTERTEK TESTING SERVICES NA, cont.

The above samples comply with the following acceptance criteria:

1. The presence of the additive or flushing agent shall not cause an increase of refrigerant and/or lubricant decomposition when compared to the neat samples via rank order analysis* of total acid increases.
2. The presence of the additive or flushing agent shall not cause an increase of corrosion or copper plating of the tested metal coupons when compared to those tested in the neat samples via rank order analysis*.
3. The presence of the additive or flushing agent shall not cause an increase in particle, precipitates, or insolubles in the sealed tubes when compared to those tested in the neat samples via rank order analysis*.

*Rank order analysis is defined as ordering both the three control groups' and the three samples' numeric results. A test failure is defined as a total separation of the numeric results of the sample and control groups where the sample's results negatively affected the desirable properties of the flushing agent or process fluid. A pass test is defined as having overlapping sets of numeric results of the sample and control groups, or a total separation of the numeric results of the sample and the control groups where the samples' results positively affected the desirable properties of the flushing agent or process fluid.

Project No.: 3118569

Appendix B

Nonmetallic Materials Compatibility

Tube ID	Refrigerant	Lubricant	Additive	Visual Inspection, liquid phase	Particles/Precipitates/ Insolubles		
Control	134a	¼ PAG ¼ Mineral Oil	Blank	0	None	None	None
Ice Cold	134a	¼ PAG ¼ Mineral Oil	Ice Cold	0	None	None	None

Physical Properties

	PTFE Skived Sheet*			Nylon 66*			Polyester*			HBNR O-ring**			Neoprene WRT O-ring**			NBR O-ring +			EPDM O-ring**		
Hardness	100	99	100	100	100	100	98	99	99	76	73	75	69	76	76	74	74	73	74	75	74

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



INTERTEK TESTING SERVICES NA, cont.

Volume (in cm ³)	.81	.82	.79	.83	.84	.83	.85	.86	.86	.85	.85	.86	.85	.87	.86	.82	.84	.83	.85	.85	.85
------------------------------	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----

*Shore Durometer D
**Shore Durometer A

Ice Cold Sample

	PTFE Skived Sheet*			Nylon 66*			Polyester*			HBNR O-ring**			Neoprene WRT O-ring**			NBR O-ring**			EPDM O-ring**		
Hardness	99	99	99	100	100	100	100	99	99	75	75	77	76	76	74	74	73	73	75	76	76
Volume (in cm ³)	.81	.80	.79	.82	.83	.83	.86	.86	.85	.84	.85	.86	.87	.85	.85	.83	.82	.82	.85	.83	.81

*Shore Durometer D
**Shore Durometer A

The above samples comply with the following acceptance criteria:

1. The presence of the additive or flushing agent shall not cause an increase or decrease in hardness when compared to those tested in the neat oil via rank order analysis*.
2. The presence of the additive or flushing agent shall not cause an increase in particles, precipitates, or insolubles in the sealed tubes when compared to those tested in the neat oil via rank order analysis*.
3. The presence of the additive or flushing agent shall not cause an increase or decrease in volume when compared to those tested in the neat oil via rank order analysis*.

*Rank order analysis is defined as ordering both the three control groups' and the three samples' numeric results. A test failure is defined as a total separation of the numeric results of the sample and control groups where the sample's results negatively affected the desirable properties of the flushing agent or process fluid. A pass test is defined as having overlapping sets of numeric results of the sample and control groups, or a total separation of the numeric results of the sample and the control groups where the samples' results positively affected the desirable properties of the flushing agent or process fluid.

Project No.: 3118569
Appendix C

Viscosity Testing

Tube ID	Lubricant	Additive	Viscosity @ 40°C			Viscosity @ 100°C		
Control	¾ PAG ¼ Mineral Oil	N/A	92.55	92.61	92.18	9.58	9.42	9.45
			92.45			9.49		
Ice Cold	¾ PAG ¼ Mineral Oil	Ice Cold	92.41	92.51	92.38	9.38	9.25	9.33
			92.43			9.32		
		% Difference	<1			1.79		

INTERTEK TESTING SERVICES NA, cont.

The above samples comply with the following acceptance criteria:

1. The presence of the additive or flushing agent shall not cause a change of kinematic viscosity more than 5% when compared to the neat sample.

Appendix D

Wear Testing, Falex

Tube ID	Refrigerant	Lubricant	Additive	Run	Pin weight loss (grams)	V-Block Wear Scarring (microscopically)
Control	R-134a	PAG	None	1	0.1025	Minimal
				2	0.1170	Minimal
				3	0.0885	Minimal
Ice Cold	R-134a	PAG	Ice Cold	1	0.0561	Minimal
				2	0.0463	Minimal
				3	0.0590	Minimal

The above samples comply with the following acceptance criteria:

1. The presence of the additive or flushing agent shall not cause an increase in pin weight loss when compared to the neat samples via rank order analysis.
2. The presence of the additive or flushing agent shall not cause an increase of block wear scar measured microscopically, when compared to the neat samples via rank order analysis

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

